

$n_d = 2.02204$ $v_d = 29.06$
 $n_e = 2.03035$ $v_e = 28.84$

$n_F - n_C = 0.035170$
 $n_F - n_C' = 0.035721$

LASF35 022291.541

| Refractive Indices | | |
|--------------------|----------------|---------|
| | λ [nm] | |
| $n_{2325.4}$ | 2325.4 | 1.95946 |
| $n_{1970.1}$ | 1970.1 | 1.96639 |
| $n_{1529.6}$ | 1529.6 | 1.97472 |
| $n_{1060.0}$ | 1060.0 | 1.98624 |
| n_l | 1014.0 | 1.98786 |
| n_s | 852.1 | 1.99531 |
| n_r | 706.5 | 2.00628 |
| n_C | 656.3 | 2.01185 |
| $n_{C'}$ | 643.8 | 2.01343 |
| $n_{632.8}$ | 632.8 | 2.01493 |
| n_D | 589.3 | 2.02173 |
| n_d | 587.6 | 2.02204 |
| n_e | 546.1 | 2.03035 |
| n_F | 486.1 | 2.04702 |
| $n_{F'}$ | 480.0 | 2.04916 |
| n_g | 435.8 | 2.06805 |
| n_h | 404.7 | 2.08663 |
| n_l | 365.0 | |
| $n_{334.1}$ | 334.1 | |
| $n_{312.6}$ | 312.6 | |
| $n_{296.7}$ | 296.7 | |
| $n_{280.4}$ | 280.4 | |
| $n_{248.3}$ | 248.3 | |

| Internal Transmittance τ_i | | |
|---------------------------------|------------------|------------------|
| λ [nm] | τ_i [10 mm] | τ_i [25 mm] |
| 2500 | 0.86 | 0.69 |
| 2325 | 0.950 | 0.88 |
| 1970 | 0.989 | 0.972 |
| 1530 | 0.997 | 0.992 |
| 1060 | 0.996 | 0.990 |
| 700 | 0.991 | 0.978 |
| 660 | 0.988 | 0.970 |
| 620 | 0.985 | 0.962 |
| 580 | 0.979 | 0.950 |
| 546 | 0.965 | 0.920 |
| 500 | 0.920 | 0.81 |
| 460 | 0.83 | 0.63 |
| 436 | 0.74 | 0.47 |
| 420 | 0.63 | 0.32 |
| 405 | 0.49 | 0.17 |
| 400 | 0.43 | 0.12 |
| 390 | 0.30 | 0.05 |
| 380 | 0.16 | 0.01 |
| 370 | 0.06 | |
| 365 | 0.03 | |
| 350 | 0.01 | |
| 334 | | |
| 320 | | |
| 310 | | |
| 300 | | |
| 290 | | |
| 280 | | |
| 270 | | |
| 260 | | |
| 250 | | |

| Relative Partial Dispersion | |
|-----------------------------|--------|
| $P_{s,t}$ | 0.2118 |
| $P_{C,s}$ | 0.4701 |
| $P_{d,C}$ | 0.2899 |
| $P_{e,d}$ | 0.2364 |
| $P_{g,F}$ | 0.5982 |
| $P_{i,h}$ | |
| $P'_{s,t}$ | 0.2086 |
| $P'_{C,s}$ | 0.5073 |
| $P'_{d,C'}$ | 0.2409 |
| $P'_{e,d}$ | 0.2327 |
| $P'_{g,F'}$ | 0.5291 |
| $P'_{i,h}$ | |

| Deviation of Relative Partial Dispersions ΔP from the "Normal Line" | |
|---|---------|
| $\Delta P_{C,t}$ | -0.0009 |
| $\Delta P_{C,s}$ | -0.0006 |
| $\Delta P_{F,e}$ | 0.0006 |
| $\Delta P_{g,F}$ | 0.0033 |
| $\Delta P_{i,g}$ | |

| Constants of Dispersion Formula | |
|---------------------------------|-----------------------------|
| B_1 | $2.45505861 \cdot 10^{+00}$ |
| B_2 | $4.53006077 \cdot 10^{-01}$ |
| B_3 | $2.38513080 \cdot 10^{+00}$ |
| C_1 | $1.35670404 \cdot 10^{-02}$ |
| C_2 | $5.45803020 \cdot 10^{-02}$ |
| C_3 | $1.67904715 \cdot 10^{+02}$ |

| Constants of Formula dn/dT | |
|------------------------------|------------------------|
| D_0 | $1.43 \cdot 10^{-07}$ |
| D_1 | $8.71 \cdot 10^{-09}$ |
| D_2 | $-2.71 \cdot 10^{-11}$ |
| E_0 | $1.02 \cdot 10^{-06}$ |
| E_1 | $1.50 \cdot 10^{-09}$ |
| $\lambda_{TK} [\mu m]$ | 0.263 |

| Color Code | |
|--------------------------|------|
| λ_{40}/λ_5 | -/37 |

| Remarks | |
|---------|--|
| | |
| | |
| | |

| Temperature Coefficients of Refractive Index | | | | | | |
|--|---------------------------------------|-----|-----|---------------------------------------|-----|-----|
| [°C] | $\Delta n_{rel}/\Delta T [10^{-6}/K]$ | | | $\Delta n_{abs}/\Delta T [10^{-6}/K]$ | | |
| | 1060.0 | e | g | 1060.0 | e | g |
| -40/-20 | 2.6 | 5.0 | 7.8 | -0.1 | 2.2 | 5.0 |
| +20/+40 | 2.7 | 5.5 | 9.0 | 1.0 | 3.8 | 7.1 |
| +60/+80 | 2.8 | 5.9 | 9.7 | 1.4 | 4.5 | 8.3 |

| Other Properties | |
|---------------------------------|-------|
| $\alpha_{-30/+70} [10^{-6}/K]$ | 7.4 |
| $\alpha_{+20/+300} [10^{-6}/K]$ | 8.5 |
| Tg [°C] | 774 |
| $T_{10}^{13.0} [°C]$ | |
| $T_{10}^{7.6} [°C]$ | |
| $c_0 [J/(g \cdot K)]$ | 0.445 |
| $\lambda [W/(m \cdot K)]$ | 0.920 |
| $\rho [g/cm^3]$ | 5.41 |
| $E [10^9 N/mm^2]$ | 132 |
| μ | 0.303 |
| $K [10^{-6} mm^2/N]$ | 0.73 |
| $HK_{0.1/20}$ | 810 |
| HG | |
| B | 2 |
| CR | 1 |
| FR | 0 |
| SR | 1.3 |
| AR | 1 |
| PR | 1.3 |